



FASTRACK Orange

Standard Grade (SG) woven geotextile

Based on our popular 609 geotextile, FASTRACK Orange prevents the intermixing of contaminated and uncontaminated soils and its bright colour also alerts users and future users to the potential danger of further excavation. It is designed and manufactured to conform to the old Department of Transport & Highways specification for road and earthworks separation.

Applications for FASTRACK Orange:

- Highly visible 'Warning layer'
- Separating/Strengthening - layer under access roads and areas of hard standing
- Separation – layers under stone foundations for new buildings
- Separation – layers under new roads, car parks & industrial areas
- Separation – granular fill from sub soils and other fill types



Mechanical properties	Test	Units	FASTRACK Orange
Tensile strength - MD	EN ISO 10319	kN/m	16
Tensile strength - XD	EN ISO 10319	kN/m	11.5
Elongation at break - MD	EN ISO 10319	%	18.5
Elongation at break - XD	EN ISO 10319	%	18.5
CBR puncture resistance	EN ISO 12236	N	1500
Hydraulic properties			
Water flow normal to the plane	EN ISO 11058	l/m ² /s	17
Characteristic opening (pore) size	EN ISO 12956	µm	250
Physical properties			
Thickness under 2 kPa	EN ISO 9863-1	mm	0.4
Weight	EN ISO 9864	g/m ²	75
Roll width		cm	450
Roll length		m	100



Other grades of geotextiles within the Fibrelok range include:
High Flow and High Strength woven fabrics and Thermal-bonded & Needle Punched non-wovens.

Fibrelok Ltd reserves the right to alter product specifications without prior notice.

It is the responsibility of all users to satisfy themselves that the above data is current.

The above figures are average values obtained in testing to current EN geotextiles test standards. Although not guaranteed these results do, to the best of our knowledge, offer a true and accurate record of the product's performance.

Polypropylene is the constituent polymer used in the production of Multitrack products.

Fibrelok cannot be held responsible for the performance of these products as conditions of use are beyond our control.

Installation details are available on request.

T: 01302 220330

E: sales@fibrelok.co.uk